



Florida: (954)973-4528 - Out-Of-State: (800)952-5980 - Fax: (954)973-4928  
 E-Mail: [sales@advancedsurfaces.com](mailto:sales@advancedsurfaces.com) Web Site: [www.advancedsurfaces.com](http://www.advancedsurfaces.com)  
 2000 Banks Road • Margate, Florida 33063

Apply when surface and ambient temperatures are above 55° & below 90°F.



# ROCK GLAZE SOLVENT BASED

A one-step coating used for sealing epoxy Chattanooga and other epoxy-bonded stone systems.

Restores and brightens.

Resists U/V rays.

Surface must be **COMPLETELY** dry prior to application.

SKID GUARD CAN BE ADDED TO SEALER TO REDUCE SLIPPING  
 5 gal. #203110 1 gal. #203111



# CHATTY GL SOLVENT BASED

This solvent based acrylic clear sealer is best used over concrete Chattanooga or any other concrete surface that already has a build-up of sealer present.

Protects and provides a durable long lasting finish.

Less solid content than Chatty 250.

Surface must be clean and dry prior to application.

SKID GUARD CAN BE ADDED TO SEALER TO REDUCE SLIPPING  
 5 gal. #203130



# CHATTY 250 SOLVENT BASED

This non-yellowing solvent based acrylic clear sealer is best used to seal concrete Chattanooga or any other porous concrete surface.

Protects from grease, oil, and damaging U/V rays.

Surface must be clean and dry prior to application.

SKID GUARD CAN BE ADDED TO SEALER TO REDUCE SLIPPING  
 5 gal. #203120 1 gal. #203121

APPROXIMATE COVERAGE: 150-200 SQ. FT. PER GALLON PER COAT  
 DEPENDING ON POROSITY OF THE SURFACE BEING SEALED

APPROXIMATE DRYING TIME	
To touch:	1 hours
Recoat:	1-2 hours
Foot Traffic:	24 hours
Heavy Traffic:	72-96 hours

**NOTE: NEWLY POURED CONCRETE MUST CURE FOR AT LEAST 28 DAYS PRIOR TO STAINING OR SEALING. NEVER APPLY A SOLVENT BASED SEALER OVER A WATER BASED PRODUCT. SURFACE MUST BE COMPLETELY DRY. DO NOT APPLY IF RAIN IS EXPECTED WITHIN 6-12 HRS FOLLOWING APPLICATION.**