

2000 Banks Road • Margate, Florida 33063
Decorative Concrete • Products & Systems



Portion Pak

Epoxy Resin & Cure
Mixes 150 lb. (3 - 50 lb. bags)
of stone or 100 lb. bag of
Texas Grit

INSTRUCTIONS FOR INSTALLING Epoxy Chattahoochee/Natural Stone

1. Surface must be clean and dry. Pressure cleaning is recommended. Make sure the sprinkler system is turned off.
2. If the deck area is not screened or walled in, wood forms should be installed around the perimeter of the deck. Forms should be oiled or greased lightly to prevent the epoxy from sticking to the form.



Economy Epoxy Kit

2 Resin & 1 Cure

(5 Gal. Containers)
Equal to 16 Portion Paks

3. Using Portion Pak Mix all of Part A - Resin (80 oz.) with all of Part B -Cure (40 oz.) thoroughly for three to five minutes in a 5 gal. Pail using a wood or metal stake. Then mix the epoxy with three 50 lb. bags of rock (Or 1 -100 lb bag of Texas Grit) being careful to coat all rocks with epoxy mix. **Approximate 15 to 20 minutes pot life after mixing.**
4. Using a steel garden bow rake, spread the rock evenly (approx. 1/2" to 3/4" thick) over the concrete surface. Using a steel trowel, trowel the rock flat by packing the stone as you trowel. You will need to wipe the trowel frequently using a clean white rag and Advanced Solvent TG. The rock when finished should be approximately 3/8" to 1/2" in thickness.
5. Do not allow any person or pets to walk on the Chattahoochee/Natural Stone for 12 hours. Remove all the wood forms. Make sure the sprinkler system is turned off.

COVERAGE:

Three (3) 50 pound bags Mix 1 Portion Pak: Part A (Resin) & Part B (Cure) will cover approximately 30 to 33 sq. ft. Economy Epoxy Kit (One five gal "cure" and two five gal. resin = 15 gal.) coverage approx 528 sq. ft. with 48 fifty pound bags of stone.

One (1) 100 pound bag

Mix 1 Portion Pak: Part A (Resin) & Part B (Cure). Approximate coverage 30 to 33 sq. ft.

PRECAUTIONS:

- Never try to install epoxy Chattahoochee when the outside temperature is below 60° F.
- Make sure you choose a day when rain is not in the forecast.
- PVC gloves should be worn while mixing and troweling.
- Clean tools with Advanced Solvent TG.
- Remove forms only after the epoxy has hardened.
- Keep epoxy and solvent out of the reach of children.



Solvent TG

Blend of mineral spirits and toluene. Used for wiping the trowel when installing epoxy stone. Otherwise, the epoxy will stick to the trowel.

Advanced Surfacing Systems

Pool Decks • Patios • Driveways • Walkways • Entrances



Advanced Surfaces
Rock Glaze Sealer



1 Gallon.

5 Gallon

- Urethane clear coating
- Resists ultraviolet rays

Natural Stone-Chattahoochee should be sealed every 10 to 12 months.

ADVANCED SURFACES
INC.
Since 1979

Showroom • Warehouse • Office
2000 Banks Road • Margate, FL 33063
Local: 954-973-4528
Out Of Area: 800-952-5980
Fax: 954-973-4926

Visit Us: www.advancedsurfaces.com
Email: sales@advancedsurfaces.com